

Typical Properties

Parameters	Value	Test Methods
TiO ₂ content	95%	XRF
Inorganic coating	Alumina; Zirconia	—
Organic treatment	Present	—
Moisture when packed*	0.5% max	ISO 787-2
Bulk density (tamped)	1.2g/cm ³	ISO 787-11
Oil absorption	18g/100g	ISO 787-5
pH	7.0	ISO 787-9
Specific gravity	4.1g/cm ³	ISO 787-10
Specific gravity	R2	—
CAS number	13463-67-7	—
Color index	Pigment White 6	—

AMIN CHEMI